KBG12300 12V 33Ah (C_{10})

Gel battery shows some distinctive advantages over flooded battery or AGM battery, such as super thermal stability, high deep discharge capability, good recovery from deep discharge , even if the battery is left discharged for three days, it will recover to 100% of capacity. With the above-mentioned advantages, the gel battery has long service life, specially suitable for motive power applications, such as golf trailer, scrubber, folklift, etc.The deep discharge cycles increased 50% as compared with the AGM battery.

Performance Characteristics

Nominal Voltage	12V	
Design Life	10 years	
Dimensions	Length (mm / inch)	195±2 / 7.68
	Width (mm / inch)	130±2 / 5.12
	Height (mm / inch)	167±2 / 6.57
	Total Height (mm / inch)	167±2 / 6.57
Approx. Weight	(Kg / lbs)	10.0 / 22.0
Terminal	M6	
Container Material	ABS	
Rated Capacity	33.0Ah / 3.30A	(10hr, 1.8V / cell, 25ºC / 77ºF)
	26.3Ah / 8.75A	(3hr, 1.75V / cell, 25ºC / 77ºF)
	21.6Ah / 21.6A	(1hr, 1.65V / cell, 25ºC / 77ºF)
Max. Discharge Current	396A (5s)	
Internal Resistance	Approx 13.2mΩ	
Operating Temp. Range	Discharge : -40 ~ 60ºC (-40 ~ 140ºF)	
	Charge : -20 ~ 50ºC (-4 ~ 122ºF)	
	Storage : -20 ~ 50ºC (-4 ~ 122ºF)	
Cycle Use	Initial charging current less than 8.3A	
	Voltage: 14.4V ~ 15.0V at 25ºC (77º F)	
	Temp. Coefficient:-30mV/ºC	
Standby Use	No limit on Initial Charging Current Voltage	
	13.5V ~13.8V at 25ºC (77º F)	
	Temp. Coefficient: -18mV/ºC	
Capacity affected by Temperature	40ºC (104ºF)	103%
	25ºC (77ºF)	100%
	0ºC (32ºF)	86%
Self Discharge	Fully charged Kaise Gel Series batteries may be stored for up to9 months at 25ºC (77ºF) and then a freshening charge is required. For higher temperatures the time interval will be shorter.	

Discharge Constant Current (Amperes) at 25ºC (77ºF)

Volts/cell	15min	30min	1h	2h	3h	5h	10h	20h
1.80V	51.9	33.8	20.6	11.9	8.68	5.74	3.30	1.76
1.75V	55.6	35.3	21.2	12.1	8.75	5.89	3.32	1.77
1.70V	57.5	35.6	21.5	12.3	8.84	5.96	3.35	1.78
1.65V	58.8	36.2	21.6	12.4	8.97	6.02	3.38	1.79
1.60V	60.6	36.9	21.8	12.5	9.06	6.09	3.41	1.80

Dimensions and Terminal (Unit: mm (inches))



Applications

Wind and solar energy systems
Cable TV systems
Telecommunications
Electric wheel chairs
Military equipment
Emergency lighting
Power plants
Medical equipment
Golf carts

Certifications

ISO 9001 / ISO 14001

Discharge End Voltage vs. Discharge Current

Final discharge voltage V/CELL	1,8	1,75	1,7	1,6
Discharge current (A)	I ≤ 0,1CA	0.25CA ≥ I > 0.1CA	0.55CA ≥ I > 0.25CA	I > 0.55CA

Discharge Constant Power (Watts per cell) at 25ºC (77ºF)

Volts/cell	15min	30min	1h	2h	3h	5h	10h	20h
1.80V	97.4	64.2	39.9	23.3	16.8	11.2	6.30	3.49
1.75V	103	65.8	40.2	23.3	16.8	11.3	6.37	3.51
1.70V	104	66.1	40.5	23.5	16.9	11.4	6.44	3.52
1.65V	105	66.1	40.9	23.5	17.0	11.5	6.50	3.54
1.60V	107	66.7	41.2	23.6	17.2	11.5	6.57	3.56

(Note) The above characteristics data are average values obtained within three charge/discharge cycles not the mimimum values.

KBG12300 12V 33Ah (C_{10})

Charging Characteristics (cycle use)



Discharge characteristic



The effect of temperature on capacity



The effect of discharge depth on cycle life



Curves of self-discharge



Curves of open circuit voltage vs. capacity



IMPORTANT NOTE: The specifications presented herein are subject to revision without notice.

2025/V1/K

Contacto
customer.energy@tempelgroup.com
www.tempelgroup.com

Tempel Group en el mundo
HOUSTON · BARCELONA · MADRID · VALENCIA · BILBAO · SEVILLA · LISBOA · PORTO · ROMA · BUENOS AIRES · LIMA
SANTIAGO DE CHILE · BOGOTÁ · SÃO PAULO · CIUDAD DE MÉXICO · MONTERREY · CIUDAD DE PANAMÁ · MONTEVIDEO · QUITO